
650S Niru[®] Cushion-Ease™ Nitrile



- 100% nitrile rubber compound, oil proof with holes for excellent drainage and aeration leaving a dry, clean work area.
- This interlocking mat allows on-site customization. Square snap together units of 91x91 cm that can be assembled effortlessly and laid out from wall to wall or as islands in any direction or shape.
- Compatible with patented MD-Ramp System™ for smart safety bevelling solutions. Allow out and inside corners.
- Superb anti-fatigue properties due to its unique design underneath and high quality resilient rubber compounds.
- Designed to yield a long service life.
- Resistant to most chemicals and extreme temperatures.
- Free of silicone therefore safe for vehicle painting facilities.











650S Niru[®] Cushion-Ease™ Nitrile

	Pl	RODUCT SPECIFICATIONS	
Designation	Industrial matting		
Туре	Anti-fatigue		
Description	Modular system, open construction		
Material	100% nitrile rubber compound		
Process	Compression moulding		
Category	Best		
Recommended use	Heavy duty – wet/dry industrial environmentss		
Colours	Black		
Weight	14,5 kg/m ²		
Thickness	19 mm		
Standard sizes	91 cm x 91 cm		
Custom sizes	N/A		
Special remarks	Accessories: MD Ramp System™ male and female attachable bevels 91 cm, black or yellow.		
		PRODUCT TESTING	
W////	Tests	Norms	Results
Compression deflection		U.S.	
*	1.4 kg/cm ²		
	2.8 kg/cm ²		
Foam battery		ASTM D3574	
Abrasion resistance		ASTM D3374 ASTM D3884-01	
ADIASION TESISTANCE	500 Cycles	A31W D3004-01	
	5000 Cycles		1.76% weight loss
Static coefficient of friction		ASTM C1028-96	0.83
		ASTM C1028-96 ASTM D412	146.7%
Elongation Breaking load		ASTM D412	140.7 /0
Graves tear strength		ASTM D412 ASTM D 1004	
Hardness		ASTM D 1004 ASTM D2240-02	55 Shore A
		DIN 51130 and BG-RULE BGR181	22 211016 V
Anti-slip		MATERIAL ANALYSIS	
Compression Cot @20	-0/	ASTM D395	2.09%
Compression Set @25%			
Compression deflecti		ASTM D575	17.9 lb/in²
Compression deflection @ 50% Standard method for rubber deterioration		ASTM D575	63.6 lb/in²
Standard method for rubber detenoration		ASTM D1171	Rating 0 - no cracking
	0.11 1 11 10	FIRE TESTING	
	Critical radiant flux	ASTM E-648	
	Fire retardancy	DIN4102	
	m 1.77	EN 13501-1	
	Flammability test	ASTM D2859	
ESD		ANSI ESD S7.1 50% Humidity	
Sustainability		Recyclable material Reach Compliant (Registration, Evaluation, Authorization ar Restriction of Chemicals)	

